



Technical Datasheet

Compound: VGPM20

Version:

2

Date of Last Alteration:

03/04/19

Overview:

A general purpose silicone moulding compound with very good mechanical properties. Special features include heat stability inside a wide temperature range. This compound has good flexibility and high transparency. It is easily pigmented to a variety of colours.

Features:

- FDA compliant to 21 CFR 177.2600
- WRc approved to M103580/A-H
- Compliant to EC1935/2004
- BfR compliance chapter XV
- Certified to USP Class VI
- Free from Phthalate
- Free from TSE/BSE bi-products.

Property	Inspection Method	Value
Temperature Range		-50°C to + 180°C (working) Up to 200°C (intermittent)
Appearance		Transparent
Density at 20°C	ISO 1183-1 A	Approx. 1.11 g/cm ³
Hardness Shore A	DIN 53505	24
Tensile Strength	DIN 53504 S1 / ISO 37	9.00 N/mm ²
Elongation at Break	DIN 53504 S 1	1000%
Tear Strength	ASTM D 624 B	30 N/mm
Rebound Resilience	DIN 53512	41%
Compression Set	DIN ISO815-B (22h / 175°C)	28%

*These figures are intended as a guide and should not be used in preparing specifications.

**Size tolerance to ISO 3302-1: 2014

Viking Extrusions Ltd

4 Ivy Arch Road, Worthing
West Sussex, BN14 8BX
Tel: +44 (0) 1903 205 532
Fax: +44 (0) 1903 205 534
www.vikingextrusions.co.uk

