



# Technical Datasheet

## Compound: VGD33

Version: 3  
Date of Last Alteration: 29/04/19

### Overview:

Silicone rubber can be expanded into silicone sponge by using blowing agents. The resulting sponge has a fine non-interconnecting cell structure encapsulated by a soft, smooth, outer skin. Silicone sponge is an excellent sealing medium, due to its stable chemical structure and good recovery.

### General Properties:

- Minimal water absorption (IP65-66 achievable)
- Resistance to ultraviolet light and corona is good
- Resistance to arcing and ozone is good
- Oxidation is virtually non-existent
- Excellent for vibration damping and cushioning components
- Generally resistant to moderate or oxidising chemicals
- Excellent heat insulation

Property	Value
Density (lb/ft <sup>3</sup> )	33 ± 4
Density (kg/m <sup>3</sup> )	550 ± 60
Elongation at Break (%)	245
Compression Set (%)	10
Force at Break (N)	160
Max Temperature (°C)	225-250
Min Temperature (°C)	-60
Toxicity NES 711 Iss. 3	N/A
Smoke Index NEX 711 Iss. 2	N/A
Burn Rate BS4735: 1974	N/A
Thermal Conductivity	N/A

\*These figures are intended as a guide and should not be used in preparing specifications.

\*\*Size tolerance to ISO 3302-1: 2014

### Colour:

The standard colour of silicone sponge is off-white, but it can be supplied in a variety of colours on request, subject to minimum order.

### RoHS Compliance:

We certify that our silicone sponge is RoHS compliant, and does not contain Lead, Mercury, Hexavalent Chromium, Cadmium, Polybrominated Biphenyls or Polybrominated Diphenyl Ethers

### Viking Extrusions Ltd

4 Ivy Arch Road, Worthing  
West Sussex, BN14 8BX  
Tel: +44 (0) 1903 205 532  
Fax: +44 (0) 1903 205 534  
[www.vikingextrusions.co.uk](http://www.vikingextrusions.co.uk)

