



Technical Datasheet

Compound: VTHT80

Version: 1
Date of Last Alteration: 21/03/19

Overview:

A high temperature rated compound with good mechanical properties. The compound has a natural cream colour and does not pigment easily. Pigmentation not recommended for use at high temperatures.

Features:

- FDA compliant to 21 CFR 177.2600

Property	Inspection Method	Value
Temperature Range		-50°C to + 300°C (max)
Appearance		Off White
Density at 20°C	ISO 1183-1 A	Approx. 1.20 g/cm ³
Hardness Shore A	DIN 53505	79
Tensile Strength	DIN 53504 S1 / ISO 37	10 N/mm ²
Elongation at Break	DIN 53504 S 1	420%
Tear Strength	ASTM D 624 B	26 N/mm
Rebound Resilience	DIN 53512	53%
Compression Set	DIN ISO815-B (22h / 175°C)	57%

*These figures are intended as a guide and should not be used in preparing specifications.

**Size tolerance to ISO 3302-1: 2014

Viking Extrusions Ltd

4 Ivy Arch Road, Worthing
West Sussex, BN14 8BX
Tel: +44 (0) 1903 205 532
Fax: +44 (0) 1903 205 534
www.vikingextrusions.co.uk



Certificate Number: FM40230