

# BISCO® HT-6240SH

## 'Glass Clear' Silicone Rubber Sheet

### General Information

BISCO® HT-6240 transparent solid silicone is a part of the performance grade series designed to handle the most demanding gasketing applications. Its unique high clarity solves aesthetic concerns within various industrial and handheld device markets. Beyond the transparency feature, the material shares similar properties to its softer counterparts, including high tear strength and extremely tight thickness tolerances.

Features and benefits:

- Product transparency improves aesthetics
- High tear strength and extremely tight thickness tolerances for gasket integrity
- Resistance to UV, ozone, extreme temperatures, and most fluids for consistency performance across many environments.

### Material Properties

#### Physical

Property	Test Method	Typical Value*	Specification**
<b>Colour</b>	Visual	Transparent	-
<b>Thickness, mm (inches)</b>	Internal	<b>0.250 – 3.18</b> <b>(0.010 – 0.125)</b>	-
<b>Specific Gravity, g/cm<sup>3</sup></b>	Internal	1.07	-
<b>Durometer, Shore A</b>	ASTM D2240	41	<b>40 ± 5</b>
<b>Compression Set, %</b>	ASTM D395 150°C (302°F / 70 hrs / 25%)	<35	-
<b>Tensile Strength, MPa (psi)</b>	ASTM D412	7.17 (1040)	<b>&gt;4.8</b> <b>(&gt;700)</b>
<b>Elongation, %</b>	ASTM D412	325	<b>&gt;200</b>
<b>Tear Resistance, ppi</b>	ASTM D624	112	<b>&gt;70</b>

Specification values in bold are tested on a batch basis.

Further industry specifications tested in the tables below.

#### Electric

Property	Test Method	Typical Value*	Specification**
<b>Dielectric Strength, Volts/mil</b>	ASTM D149	386	-
<b>Dielectric Constant, 1 kHz</b>	ASTM D150	2.76	-
<b>Dissipation Factor, 1 kHz</b>	ASTM D495	0.003	-
<b>Dry Arc Resistance, Seconds</b>	ASTM D495	124	-
<b>Volume Resistivity, Ω·cm</b>	ASTM D257	10 <sup>14</sup>	-

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. The information contained within this data sheet is subject to change without notice.


Viking Extrusions Ltd – Ivy Arch Road, Worthing, West Sussex, BN14 8BX, UK

Company Number: 2634482UK

VAT Number: GB587651394

Registered in England & Wales

REV 01 – Last Updated: 25/06/24



# BISCO® HT-6240SH

## 'Glass Clear' Silicone Rubber Sheet

### Thermal

Property	Test Method	Typical Value*	Specification**
Temperature Range, °C (°F)	Internal	-55 to + 200 (-67 to +392)	-
Thermal Conductivity, W/m <sup>2</sup> K	ASTM D518	0.21	-
Low Temperature Brittleness	ASTM D2137 -62°C (-80°F) / 3 min	Pass	-

### Standard Thickness Tolerances

Nominal Thickness mm (inches)	Tolerance mm (inches)
0.254 (0.010)	± 0.051 (± 0.002)
0.508 (0.020)	+0.076/-0.051 (+0.003/-0.002)
0.787 (0.031)	± 0.102 (± 0.004)
1.600 (0.063)	± 0.152 (± 0.006)
3.175 (0.125)	± 0.203 (± 0.008)

### Slit Material and Tape (PSA) Width Tolerances

Nominal Width mm (inches)	Tolerance mm (inches)
> 0 – 76 (> 0 – 3)	± 1.60 (± 0.063)
> 76 – 206 (> 3 – 8)	± 2.39 (± 0.094)
> 203 – 305 (> 8 – 12)	± 3.18 (± 0.125)
> 305 – 457 (> 12 – 18)	± 4.78 (± 0.188)
> 457 – 660 (> 18 – 26)	± 5.56 (± 0.219)
> 660 – 914 (> 26 – 36)	+25.4/-0 (+1/-0)

### Linear

Material is shipped between one or two clear PET carries for easy handling based on product thickness. Linear must be removed prior to die cutting to allow the material to shrink and relax.

### Value Added Offerings

- Adhesive (PSA) lamination on ≥ 0.787mm (0.031")
- Slit material tapes

Thickness mm (inches)	Construction Linear type
<0.787 (0.031)	PET Liner Two Sides
>0.787 (0.031)	PET Liner One Side

Notes:

\*Typical Value- Value is based on historical data. Please note the frequency of testing varies. \*\*Specification- Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values. Additional industry specifications are available as well. All other properties are based on industry standard guidelines.

BISCO® Datasheet available [here](#)

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for their intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. The information contained within this data sheet is subject to change without notice.

Viking Extrusions Ltd – Ivy Arch Road, Worthing, West Sussex, BN14 8BX, UK

Company Number: 2634482UK

VAT Number: GB587651394

Registered in England & Wales

REV 01 – Last Updated: 25/06/24

